

SUPEROX[®] 46-753

DESCRIPTION

Superox[®] 46-753 is a solution of methyl ethyl ketone peroxides and cumyl hydroperoxide in phlegmatizer. Superox[®] 46-753 is a liquid polymerization initiator for the room temperature cure of specialized unsaturated polyester and vinyl ester resins with the following advantages/properties.

- Low Peak exotherm
- Longer working time (gel time)
- Excellent final cure
- Eliminates in-plant mixing of peroxides
- Low impurity levels (water, hydrogen peroxide, MEK)

TYPICAL PROPERTIES

Active Oxygen.....	9.0 %, max.
Form	Liquid
Color	Pale Yellow
Specific Gravity @ 25°/4°C	1.07
Flash Point (SETA C.C.)	150°F/ 66°C, min.
Soluble in	Oxygenated Organic Solvents
Slightly soluble in	Water

APPLICATION

Superox[®] 46-753 is an excellent liquid polymerization initiator for the room temperature cure of unsaturated polyester and vinyl ester resins, when a low peak exotherm is desired. Gel times will be slower compared to standard Superox[®] MEKP products (i.e. 46-701, 46-747, etc.), but final cured resin hardness is often better than for resins initiated with standard MEKP's.

RESIN: Marine Laminating (pre-promoted)*

Initiator	Gel Time	Peak Exotherm	Barcol Hardness @		
			3 hrs.	5 hrs.	24 hrs.
Superox [®] 46-701	13.1 min.	349°F	55-60(5)	65-70(5)	10-15(4)
Superox [®] 46-753	40.1 min.	290°F	0-5 (D)	50-55(D)	20-25(4)
Superox [®] 46-770	29.7 min.	313°F	5-10(D)	55-60(D)	15-20(4)

Results determined by Syrgis laboratory test methods and are to be used for comparison, only.

Resin suppliers should be contacted for specific recommendations for individual resins.

SUPEROX[®] 46-753

STORAGE

- Storage at 80°F or below is recommended. Storage below 70°F is recommended for maximum shelf life.
- Store in original containers **away** from flammables and all sources of heat, sparks, or flames; out of direct sunlight; and **away** from **cobalt naphthenate**, other promoters, accelerators, oxidizing or reducing agents and strong acids or bases.
- **Leaking containers** – Remove and isolate in a safe area. Re-package or dispose immediately (see **spills**).
- **Never** store in refrigerators containing food and/or beverages.
- Consult National Fire Protection Association (NFPA) Code 432 and/or local regulatory agencies.
- Rotate stock, use oldest date first.

HANDLING

- Inform all personnel of procedures for safe handling and review MSDS with them.
- Remove from storage area only the amount needed for one shift.
- Wear safety glasses or goggles and chemical resistant gloves.
- Keep away from heat, flames, and sparks.
- Avoid breathing vapors.
- Dilution is not recommended. Never dilute with acetone.
- **Never** add peroxides directly to promoters or vice-versa, violent decomposition can occur.
- Prevent contamination such as contact with dust, over spray, wood, and combustible material.
- Avoid contact with materials other than polyethylene, polypropylene, Teflon®, Tygon®, or similar materials, glass or glass-lined steel, and 304 or 316 stainless steel or equivalent.

FIRST AID

- EYES – Flush immediately with large amounts of fresh water and continue washing for at least 15 minutes. **Medical attention is needed.**
- SKIN – Wash with soap and water.
- INGESTION – Administer large amounts of milk or water and call a physician immediately. Do not induce vomiting. As an aid to the physician, suggest calling your local Poison Control Center.

SPILLS

- Clean up immediately by absorbing with inert material – vermiculite or sand.
- After absorbing, moderately wet immediately with water and place in a clean plastic bag inside a plastic pail.
- Dispose of immediately in accordance with local, state, and federal regulations.
NOTE: Spilled peroxides, if not immediately cleaned up, can become contaminated and ignite or decompose in a hazardous, violent manner.

FIRE

- Peroxides ignite readily and burn vigorously with acceleration.
- Use water from a safe distance – preferably with a water-fog nozzle.
- For very small fires, an extinguisher with carbon dioxide, foam, or dry chemical may be effective.
- In case of fire in or near a storage area, cool stored containers with water spray.

PACKAGING, SHIPPING & AVAILABILITY

- The standard package sizes of Superox[®] 46-753 are cases of 4x8 lb. and 4x4 kg polyethylene bottles; and 40 lb. or 20 kg Hedpacks. For custom package sizes, please contact your local distributor or Syrgis Performance Initiators, Inc.
- Classification – Please refer to the specific Superox[®] 46-753 Material Safety Data Sheet under section 14, Shipping Description.
- Superox[®] 46-753 is available through a nation-wide distributor network. Call Syrgis Performance Initiators, Inc. for the name of the distributor in your area.

NOTE: MSDS's for all our products may be requested thru the website www.syrgisperformanceinitiators.com

"The information contained in this bulletin is based on information received of our staff and of others and is presented in good faith and with every belief in its accuracy. Due to the extensive technology involved in its usage, the manufacturer in no way guarantees such information, nor does he make any recommendations as to its use in the infringement of any patent. The information contained in this bulletin supersedes and replaces all information contained in all previous bulletins. Seller makes no warranty of any kind, expressed or implied, except that the goods sold hereunder shall meet the specifications of the buyer. After goods are accepted by the buyer within the time specified the buyer assumes all risk and liability for damages resulting from the use of the goods. Whether used by the buyer singly or in combination with other products, or if sold by buyer to third persons either in its original form or if repackaged by buyer and then sold to third persons."



SYRGIS PERFORMANCE INITIATORS, INC.

334 Phillips 311 Road, Helena Arkansas 72342

Tel. (800) 786-6722 • Fax (800) 987-0845 • www.syrgis.com